Supplier - ARKEMA
VPS 11
Fatty Ester Triglyceride
Vegetable Poly-Sulfdes

## **Typical Properties**

Appearance	Light Brown Fluid
Color,Gardner	< 7
Viscosity@40°C,cSt	200 - 300
Viscosity@100°C,cSt	35
Copper Corr+	≤ 1b
Sulfur Content (Active),%wt	> 10 (<1)
H <sub>2</sub> S Test,Acetate Paper Color	< 3
Specific Gravity	0.950
Average Weight,lbs/gal	7.93
Flash Point, °C	> 150
Pour Point,°C	≤ -10
$P_B / P_D + +$	80 / 250
Load Wear Index <sup>++</sup>	42
4 Ball Wear(IP239,40kg,1h),mm	0.5
Reichert Test(300N Load),mm <sup>2</sup>	1.2

<sup>&</sup>lt;sup>+</sup> 10%, 3h, 100

## **Product Description**

**VPS 11** is a light brown liquid with very slight odor and no chlorinated impurities. It is a lubricity- enhancing agent for industrial and metal working formulations, which also provides anti-wear and extreme pressure properties. It does not corrode copper alloys.

**VPS 11** is recommended for the formulation of metal working fluids especially when working with copper and its alloys. Its EPS properties are enhanced when combined with Arkema Inc.'s **TPS** products (**TPS 20** is particularly recommended).

Print date: 04-12-25

<sup>\*\* 4</sup> Ball EP, ASTM D2783, 5% in Paraffinic Base Oil