Supplier - ARKEMA
Vultac 3
Sulfur Containing Additive

Typical Properties

Suggested Treat Rate,%wt 3 - 5 Physical Form **Pastilles** Average Softening Point,°C 105 Average Sulfur Content, %wt 28 Stearic Acid,%wt NIL Compatibility Synthetic Ester/Vegetable Oil 10%Additive+90%Synthetic Easter P_B/P_D+ 61 / 620 10%Additive+90%Vegetable Oil P_B/P_D+ 76 / 620

Product Description

Vultac 3 is a poly-tert-butylphenoldisulfide-based products, with antioxidant and EP properties. It is designed for formulations in oil-based metal working fluids. The additive can be dissolved in synthetic esters or vegetable oils to make up high performance cutting oils.

Vultac 3 can be used together with high molecular polymeric esters or phosphorus containing compounds to attain synergistic effect.

Print date: 21-12-25

⁺Servo motor speed - PB:1500rpm in 0.03s, PD:1760rpm in0.03s.